

GEOGARD® LV Base Coat

#352564G802-2 gallon pails

#352564G805-5 gallon pails

High-performance, single component aromatic urethane base coat used with Geogard Finish Coat

Description

GEOGARD LV Base Coat is a high performance, single component aromatic urethane base coat, used in conjunction with GEOGARD Finish Coat as a restoration system.

Uses

The GEOGARD LV Base Coat with GEOGARD Finish Coat is used as a restoration coating system to protect and extend the life of a variety of weathered single ply roof membrane systems, smooth BUR, modified bitumen, polyurethane foam and structural concrete roofs. It is always applied in a two-coat process, as a base coat and finish coat. The GEOGARD LV Base Coat is highly elastomeric and bonds directly to the prepared surface. The GEOGARD Finish Coat is white and protects the roofing assembly from airborne pollutants, residual factory emissions, and damaging UV radiation.

Advantages

GEOGARD LV Base Coat and Finish Coats are single component products, meaning there is no blending of multi-component kits. The GEOGARD LV Base Coat and GEOGARD Finish Coat System extends the life of single-ply roofs and other roof substrates. The finish coat is reflective, resulting in lower surface temperatures, increased roof life and lower energy costs.

Limitations

Do not apply when air or surface temperature is below 50°F or above 110°F or when rain is imminent. The GEOGARD LV Base Coat and GEOGARD Finish Coat System is not intended for use in continual ponding water areas, over lightweight concrete, over non-reinforced PVC single ply systems or new single ply roof membranes. Allow new single ply roofs to age 6 months prior to application of the GEOGARD LV Base Coat and GEOGARD Finish Coat System. Do not use on roof membranes where plies have become embrittled or where the substrate or insulation has become saturated with water. Do not use over tar, silicone based coatings or gravel surfaced BUR. **Note: All EPDM membranes must be looked at individually as some EPDM formulations have a potential for membrane swelling due to**

the solvent content in GEOGARD. A test application must be conducted by applying GEOGARD LV Base Coat at 1 gal./100 sq. ft. or 16 wet mils. Check for swelling for a 12-24 hour period. If membrane swells, a very light application of GEOGARD LV Base Coat is recommended at 8 wet mils. After 24 hour cure, follow with the remainder of actual coverage rate. Recoating of GEOGARD LV Base Coat must be performed within 48 hours of initial application. Beyond that time, the GEOGARD LV Base Coat must be primed prior to the application of GEOGARD Finish Coat.

Coverage

The GEOGARD LV Base Coat and GEOGARD Finish Coat System is to be applied in two coats consisting of a Gray Base Coat and White Finish Coat. The GEOGARD LV Base Coat will be applied as follows:

Weathered Single Ply	1- 1/2 gal./100 sq. ft. (24 wet mils)
Foam	3 gal./100 sq. ft. (48 wet mils)
Concrete	3 gal./100 sq. ft. (48 wet mils)
Smooth Surface Built-Up & Modified Bitumen Roofing	3 gal./100 sq. ft. (48 wet mils)

The GEOGARD Finish Coat will be applied at a coverage rate of 1 gal./100 sq. ft. (16 wet mils) on all surfaces.

Note: Because of the irregular surface that can be encountered, the GEOGARD LV Base Coat amounts are minimum requirements and may be increased due to surface conditions.

Preparation

Surfaces must be clean and dry. Remove all loose dirt and foreign matter with a stiff broom or proper mechanical equipment. Ruptures, splits, cuts, and torn flashings shall be repaired as needed. Blisters must be cut open and allowed to dry.

Refer to appropriate specifications for detailed instructions.

Tremco always recommends a test sample applied in an area representative of conditions. A test application is the best method of determining compatibility with and adhesion to the membrane or previously coated surface. Material should be stored in an area sheltered from harsh weather conditions at temperatures ranging from 60°F to 80°F and low humidity.

Application

GEOGARD LV Base Coat and GEOGARD Finish Coat may be applied by brush, roller or squeegee. MIX WELL BEFORE USE, USING A POWER ASSISTED MIXER. Do not thin. A grid layout of the surface is recommended so that proper application quantities can be calculated as the job progresses.

TECHNICAL DATA – BASE COAT

Weight per Gallon (ASTM D 1475)	11.5 ± 0.2 lbs.
Specific Gravity	1.32 ± 0.02
Solid by Weight	74% ± 1%
Solids by Volume	65% ± 1%
Elongation (ASTM D 412)	450%
Flexibility @ 77°F (ASTM D 1737)	Passes 1/8" mandrel bend
Tensile Strength (ASTM D 412)	320 psi
Shore "A" Hardness (ASTM D 2240)	37
Dry Time (ASTM D 1640)	24 hours to tack free 48 hours to full cure
Flashpoint (Seta Flash)	>100°F
Clean Up	Pure Xylene
VOC	250 g/l



REPUBLIC
RESTORATION SYSTEMS

TREMCO

GEOGARD® LV Base Coat

Wet mil thickness must be tested with a wet mil gauge as the job progresses to assure that the dry mil thickness is achieved in all coated areas. Tremco provides on request information regarding wet and dry mil thickness, temperature, dew point, and a wet mil thickness gauge.

When applying GEOGARD LV Base Coat and GEOGARD Finish Coat over a previously coated substrate, a test patch should be applied to determine compatibility. GEOGARD LV Base Coat **MUST BE TOPCOATED** with GEOGARD Finish Coat within 24-48 hours following the application of the Base Coat. If left uncoated for more than 48 hours, the surface must be primed with GEOGARD PRIMER prior to applying the Finish Coat. Environmental conditions associated with extremes in temperature and humidity may affect cure rates and recoat limitations. Refer to application specifications for additional information.

Maintenance

It is recommended that the coating installation be checked on a regular schedule with additional inspections after the system has been exposed to severe conditions. Small area touch up can be made at any time by following recommended application procedures.

Technical Services

Technical advice or service on suitability of material for specific application and end-use requirements is available from the manufacturer. Refer to label and Material Safety Data Sheet (MSDS) for precautionary information.



Tremco Incorporated
3735 Green Road, Beachwood, OH 44122
U.S.: 800-551-7081
50 Beth Nealson Drive, Toronto, Ontario M4H 1M6
CA: 800-668-9879
www.tremcoroofing.com

GEOGARD is a U.S. registered trademark of Republic Powdered Metals, Inc.

The information provided on this data sheet is effective as of June 2015 and supersedes all previous data concerning this product and its application.

© Republic Restoration Systems by Tremco, 2015. All Rights Reserved.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCES SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.