

# AlphaGuard® PUMA Quick Flash

## **Two-Component, Polyurethane Modified Methyl Methacrylate Flashing Grade Resin**

### **FEATURES**

PUMA Technology

Low Temperature Applications

Catalyzed Cure

High Solids

Plant Root Resistance

VOC Compliant

### **BENEFITS**

- Unique technology typically provides higher elongation and crack bridging properties than comparable MMA/PMMA technology
- Product can be applied in freezing temperatures.
- Results in faster cure than one-component products
- 100% Solids
- Highly durable system prevents damage caused by plant roots in vegetative roofing installations
- 0 g/L; Can be used anywhere (No VOC restrictions)

### **DESCRIPTION:**

AlphaGuard PUMA Quick Flash is a pre-formulated high elastomeric, two-component, polyurethane modified methyl methacrylate flashing grade resin.

### **BASIC USES:**

AlphaGuard PUMA Quick Flash is used in conjunction with the AlphaGuard PUMA system to provide a flexible, waterproof membrane for flashing applications.

### **PACKAGING:**

Available in 6 gallon (22.71 L) and 2 gallon (7.57 L) containers.

### **COLOR:**

Gray

### **GRADE:**

Brush / Roller

### **POT LIFE:**

10 - 15 minutes.

*\*Pot life dependent on ambient, substrate, and product temperature and the amount of AlphaGuard PUMA Catalyst used.*

### **STORAGE LIFE:**

12 months in unopened containers. Recommended storage conditions are indoors in a ventilated, dry area removed from heat, open flame, ignition sources, and direct sunlight. Storage temperatures should range from 60-70°F (15-21°C) and must not exceed 110°F (43°C).

On the job site, materials should remain on the pallet until use and be stored in a shaded, ventilated area. Materials should be covered with a light-colored, reflective tarp for protection against the elements. Allow for adequate air flow inside the pallets.

Shelf life could be effected if the product is not stored properly.

### **APPLICATION:**

**Preparation:** Surface must be clean, dry, solid and free of dirt, grease, oil, algae, and any other debris/contaminants.

Allow new concrete to cure for a minimum of 28 days and until moisture, RH, and compressive strength values reach an appropriate level. Concrete surfaces must be shot-blasted to a an ICRI 3-6 surface profile.

# AlphaGuard® PUMA Quick Flash

**APPLICATION:**  
(continued)

Metal must be ground to a clean, bare, bright metal surface.

**Repairs:** If AlphaGuard PUMA is being installed over an existing roof system, all appropriate repairs should be made prior to applying the AlphaGuard PUMA system. Allow suggested cure time of repairs before application.

**Reinforcement:** AlphaGuard PUMA Quick Flash requires full reinforcement with Permafab (polyester membrane) or AlphaGuard Glass Mat.

**Mixing:** Use a heavy duty power drill with Jiffy Mixer attachment. Cordless drills are not recommended and may not properly mix the materials. AlphaGuard PUMA Quick Flash must be mixed to achieve a uniform distribution and appearance of the product. Once properly mixed, AlphaGuard PUMA Quick Flash can be poured off in smaller quantities into a second container. Add the appropriate amount of AlphaGuard PUMA Catalyst to the selected amount of AlphaGuard Quick Flash and mix thoroughly until powder catalyst is completely dissolved. Catalyze only the amount of AlphaGuard Quick Flash intended to be used within the expected pot life. The amount of AlphaGuard PUMA Catalyst required is based on the amount of Quick Flash used and the ambient weather conditions (Refer to the mixing chart for proper mixing ratios.).

**Application:** Apply AlphaGuard PUMA Quick Flash at 2½ gals / 100 sq. ft. (40 wet mils) minimum. Embed reinforcing fabric into wet coating using a brush or roller until free of voids, wrinkles, air pockets, etc. While coating is still wet, apply AlphaGuard PUMA Quick Flash over embedded fabric at 2½ gals / 100 sq. ft. (40 wet mils) minimum. Allow to cure prior to applying top coat.

**MIXING CHART:**

AG PUMA QUICK FLASH AMOUNT	ALPHAGUARD PUMA CATALYST AMOUNTS BY TEMPERATURE RANGES														
	70-95°F (21-35°C) 2% Catalyst			60-70°F (15-21°C) 4% Catalyst			40-60°F (5-15°C) 5% Catalyst			32-40°F (0-5°C) 6% Catalyst			< 32°F (< 0°C) 6% Catalyst + Accelerator		
	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g	oz	lbs	g
½ gal (5.71 lbs) 1.89 L (2.59 kg)	2	0.11	50	4	0.22	100	5	0.28	125	6	0.33	150	6	0.33	150
1 gal (11.43 lbs) 3.78 L (5.18 kg)	4	0.22	100	8	0.44	200	10	0.55	250	12	0.66	300	12	0.66	300
3 gal (34.29 lbs) 11.34 L (15.55 kg)	12	0.66	300	24	1.32	600	30	1.65	750	36	1.98	900	36	1.98	900
6 gal (68.58 lbs) 22.68 L (31.10 kg)	24	1.32	600	48	2.65	1,200	60	3.91	1,500	72	3.97	1,800	72	3.97	1,800

**ACCEPTABLE SURFACES/SUBSTRATES:**

Smooth BUR	Gravel BUR	Concrete	Foam	Modified Bitumen	Metal	Single Ply	SPUF	Walls
●		●		●	●			●

**COVERAGE RATE:**

5 gals / 100 sq. ft. (80 mils) in two coats with fabric reinforcement.

**CLEAN UP:**

Clean tools immediate after use with AlphaGuard PUMA Cleaner.

**LIMITATIONS:**

- Not for use over expanded polystyrene, extruded polystyrene, plywood, tongue and groove decks, wood decks, poured in place gypsum, lightweight insulating concrete, lightweight structural concrete, cementitious wood fiber decks, coal tar pitch, gravel surfaced BUR, corrugated metal roof systems, and SPUF roofing substrates.
- Do not apply in falling precipitation or when precipitation is imminent.
- Only apply when ambient temperature is -20°F - 95°F (-28°C - 35°C).

**PRECAUTIONS:**

Use Tremco AlphaGuard PUMA Quick Flash with adequate ventilation. If the product is applied in enclosed areas without natural ventilation, forced ventilation must be arranged. Avoid strong concentration of vapor as well as direct contact with skin or eyes. Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.



# AlphaGuard® PUMA Quick Flash

## MAINTENANCE:

Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

## TECHNICAL SERVICES:

Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the services of the Tremco Technical Service Staff.



7062  
01/25/17

[www.tremcoroofing.com](http://www.tremcoroofing.com)  
3735 Green Road  
Beachwood, Ohio 44122  
1.800.852.6013



50 Beth Neelson Drive  
Toronto, Ontario M4H 1M6  
1.800.668.9879

AlphaGuard is a U.S. registered trademark of Tremco, Inc.

The information provided on this data sheet is effective as of March 2016 and supersedes all previous data concerning this product and its application.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCES SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.