

GEOGARD® Finish Coat

GEOGARD Finish Coat
#4890902C – 2 gallon pails
#4890905P – 5 gallon pails

High-performance, single component aliphatic urethane finish coat used with Geogard Base Coat

Description

GEOGARD Finish Coat is a single component, moisture-cure, high-performance, aliphatic urethane finish coat and is part of a fire resistant two-coat, polyurethane, elastomeric coating system.

Uses

The GEOGARD Finish Coat is white and protects the GEOGARD Base Coat and the underlying roofing assembly from exposure to fire, airborne pollutants, residual factory emissions, and damaging UV radiation. The GEOGARD System is used as a fire resistant restoration coating to protect and extend the life of a variety of weathered single ply roof membrane systems, smooth BUR, modified bitumen, polyurethane foam and structural concrete roofs. It is always applied in a two-coat process, as a base coat and finish coat. Silica sand or aggregate may be added to GEOGARD Finish Coat to achieve a slip-resistant surface.

Advantages

GEOGARD Finish Coat is a single component product, meaning there is no blending of multi-component kits. GEOGARD Finish Coat is reflective, resulting in lower surface temperatures, increased roof life and lower energy costs. The GEOGARD System is a very versatile coating system, extending the life of a variety of roofing substrates.

Limitations

Do not apply when air or surface temperature is below 50°F or above 110°F or when rain is imminent. The GEOGARD System is not intended for use in continual ponding water areas, over lightweight concrete, over non-reinforced PVC single ply systems, new single ply roof membranes or over gravel surfaced BUR. Allow new single ply roofs to age 6 months prior to application of the GEOGARD System. Do not use on roof membranes where plies have become embrittled or where the substrate or insulation has become saturated with water. Do not use the GEOGARD System over tar, silicone based coatings, or gravel surfaced BUR.

Note: All EPDM membranes must be looked at individually as some EPDM formulations have a potential for membrane swelling due to the solvent content in GEOGARD. A test application must be conducted by applying GEOGARD Base Coat 1 gal./100 sq. ft. (16 wet mils). Check for swelling within a 12-24 hour period. If membrane swells, a very light application is recommended applying GEOGARD Base Coat at 8 wet mils. After a 24 hour cure, follow with the remainder of the required coverage rate. Recoating of GEOGARD Base Coat and/or Finish Coat must be performed 24-48 hours following the initial application. If left uncoated for more than 72 hours, the surface must be primed with GEOGARD PRIMER at 400-500 sq. ft./gal. and allowed to dry prior to applying the next coat.

Coverage

The GEOGARD System is to be applied in two coats consisting of a Gray Base Coat and White Finish Coat. GEOGARD Finish Coat must be applied over the base coat at a coverage rate of 1 gal./100 sq. ft. (16 wet mils) on all surfaces.

Preparation

Surfaces must be clean and dry. Remove all loose dirt and foreign matter with a stiff broom or proper mechanical equipment. Ruptures, splits, cuts, and torn flashings shall be repaired as needed. Blisters must be cut open and allowed to dry. Use a three-course technique for repairs to the surface. Refer to the specifications for detailed instructions.

- 1) Apply sufficient GEOGARD Base Coat over the area to be repaired so that the PERMAFAB fabric can be thoroughly embedded into the wet coating.
- 2) Embed PERMAFAB fabric reinforcement.
- 3) Apply additional GEOGARD Base Coat to completely cover and encapsulate the PERMAFAB Fabric.

Tremco always recommends a test sample applied in an area representative of conditions. A test application is the best method of determining compatibility with and adhesion to the membrane or previously coated surface. Material should be stored in an area sheltered from harsh weather conditions at temperatures ranging from 60°F to 80°F and low humidity.

Application

GEOGARD Finish Coat may be applied by brush, roller, or squeegee. MIX WELL BEFORE USE, USING A POWER ASSISTED MIXER. DO NOT THIN. A grid layout of the surface is recommended so that proper application quantities can be calculated as the job progresses. Wet mil thickness must be tested with a wet mil gauge as the job progresses to assure that the dry mil thickness is achieved in all coated areas. Tremco provides on request information regarding wet and dry mil thickness, temperature, dew point, and a wet mil thickness gauge. When applying GEOGARD over a previously coated substrate, a test patch should be applied to determine compatibility. GEOGARD Base Coat MUST BE TOPCOATED with GEOGARD Finish Coat between 24-48 hours following the application of the Base Coat. If left uncoated for more than 72

TECHNICAL DATA - FINISH COAT

| | |
|---|--|
| Weight per Gallon (ASTM D 1475) | 8.8 ± 0.2 lbs. |
| Specific Gravity | 1.06 ± 0.02 |
| Solid by Weight | 69% ± 1% |
| Solids by Volume | 51% ± 1% |
| Elongation (ASTM D 412) | 250% |
| Flexibility @ 77°F (ASTM D 1737) | Pass 1/8" mandrel bend |
| Tensile Strength (ASTM D 412) | 3,480 psi |
| Shore "A" Hardness (ASTM D 2240) | 80 |
| VOC | < 250 g/l |
| Dry Time (ASTM D 1640) | 16 hours to tack free 24 hours to full cure |
| Flashpoint (Seta Flash) | 80°F |
| Clean Up | Xylene |



REPUBLIC
RESTORATION SYSTEMS

TREMCO

GEOGARD® Finish Coat

hours, the surface must be primed with GEOGARD PRIMER prior to applying the Finish Coat. Environmental conditions associated with extremes in temperature and humidity may affect cure rates and recoat limitations. Refer to application specifications for additional information.

Maintenance

It is recommended that the coating installation be checked on a regular schedule with additional inspections after the system has been exposed to severe conditions. Small area touch up can be made at any time by following recommended application procedures.

Technical Services

Technical advice or service on suitability of material for specific application and end-use requirements is available from the manufacturer. Refer to label and Material Safety Data Sheet (MSDS) for precautionary information.



Tremco Incorporated
3735 Green Road, Beachwood, OH 44122
U.S.: 800-551-7081
50 Beth Nealson Drive, Toronto, Ontario M4H 1M6
CA: 800-668-9879
www.tremcoroofing.com

GEOGARD is a U.S. registered trademark of Republic Powdered Metals, Inc.

The information provided on this data sheet is effective as of June 2015 and supersedes all previous data concerning this product and its application.

© Republic Restoration Systems by Tremco, 2015. All Rights Reserved.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCES SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.