



Professional Roofing Products

PRODUCT ADVANTAGES

Features	Benefits
Adheres to wet surface	• Emergency repairs can be made during inclement weathers
Excellent workability	• Easily troweled - can be applied by in house crews
Sag resistant	• Can be used on vertical repairs
Fibrated	• Increases durability and longevity
Asbestos free	• Reduces future asbestos liability
Adheres to wet surface	• Can be used on asphalt and coal tar pitch substrates

Wet and Dry Asphalt Mastic

Composition: Wet and Dry Asphalt Mastic is an asphalt-based, fibrated mastic blended with penetrating oils and plasticizing agents. Wet and Dry Asphalt Mastic is asbestos free.

Basic Uses: Wet and Dry Asphalt Mastic is used for emergency repairs to asphalt roof substrates. Wet and Dry Asphalt Mastic can also be used to make temporary, emergency repairs to coal tar pitch roof membranes. Wet and Dry Asphalt Mastic can be applied to wet or dry surfaces. Reinforcing membrane can be incorporated into mastic.

Limitations: Not for use with EPDM or PVC roof membranes

Packaging: Wet and Dry Asphalt Mastic is available in 5 gallon (18.9L) and 3 gallon (11.3L) containers.

Grade: Trowel

Storage Life: One year

Application Data: Remove loose gravel, dirt, dust, rotted felts, and foreign matter. Apply over clean, sound base. Can be applied over wet or dry surfaces.

Using a roofing trowel, apply a large mass of Wet and Dry Asphalt Mastic to the area of the roof membrane in need of repair. Mound the Wet and Dry Asphalt Mastic over the repair area and smooth out to a feather edge approximately 4 to 6 inches (100 to 150 mm) on either side of the repair area.

Coverage: Emergency repairs may require as much as 1/4 to 1/2 inch (6.3 to 12.7 mm) of material over the repair area. 1/4" (6.3mm) thickness equals approximately 15 gal/100 sq ft. (6.1L/m²) Coverage rates will vary according to use.

When used as a stripping mastic, apply at 12 sq ft./gal (4.9L/m²) (approx. 1/8" (3.2 mm)) per single troweled course. Three course (mastic, reinforcement, and mastic) applications are recommended.

Precautions: Users must read container labels and Material Safety Data Sheet for health and safety precautions prior to use.

Wet and Dry Asphalt Mastic

PHYSICAL/PERFORMANCE CHARACTERISTICS

Wet and Dry Asphalt Mastic

Property	Typical Value	Test Method
Asbestos Content	None	EPA 600/R-93/116
Viscosity @ 77° F (25°C)	840,000 cP (840cP (840Pa.s))	ASTM D 2196-86
Density @ 7°F (25°C)	9.68 lb/gal. (1.16kg/l)	ASTM D 1475-90
Non-volatile matter	81.7%	ASTM D 4586-93

Availability and Cost:

Contact your local Tremco Roofing Representative for pricing and availability. For the name and number of your Representative, call the Roofing Division at 216/292-5000.

Maintenance:

Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

Technical Services:

Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the services of the Tremco Technical Service staff.

Statement of Policy and Responsibility:

Tremco takes responsibility for furnishing quality materials and for providing specifications and recommendations for their proper installation.

As neither Tremco itself nor its Representatives practice architecture or engineering, Tremco offers no opinion on, and expressly disclaims any responsibility for the soundness of any structure on which its products may be applied. If questions arise as to the soundness of a structure or its ability to support a planned installation properly, the Owner should obtain the opinion of competent structural engineers before proceeding. Tremco accepts no liability for any structural failure or for resultant damages, and no Tremco Representative is authorized to vary this disclaimer.

Tremco Incorporated warrants Wet and Dry Based Mastic to be free of defects and to meet published physical properties when tested according to ASTM and Tremco standards. Under this warranty, any Wet and Dry Asphalt Mastic that is proved to be defective when applied according to Tremco's written instructions, and in applications recommended by Tremco as suitable for this product will be replaced with like product at no charge. THIS IS BUYER'S SOLE AND EXCLUSIVE REMEDY.

Manufactured by Tremco Incorporated
3735 Green Road, Beachwood, Ohio 44122 • 1.800.852.6013

An **RPM** Company