

POWERply® HE FR Plus

A High Performance Granule Surfaced Polyester Reinforced SBS/SEBS Modified Bitumen Membrane

COMPOSITION:

POWERply® HE FR Plus is a granule surfaced, fire resistant modified bitumen membrane. It consists of specially selected bitumens, modified with compatible SBS/SEBS elastomers and reinforced with a non-woven polyester mat. POWERply HE FR Plus is furnished with a factory applied granule surfacing. POWERply HE FR Plus is asbestos free. POWERply HE FR Plus exceeds the requirements of ASTM D6164, Type II, Grade G.

BASIC USES:

POWERply HE FR Plus is designed for applications over multi-ply systems where a high strength, polyester reinforced, granule-surfaced membrane is desired.

LIMITATIONS:

- Not intended to perform under ponding conditions. Positive drainage required.
- Not to be exposed to solvents, oils, or other contaminants harmful to asphaltic materials.
- Backnail on roofs with slopes 2:12 (2" per foot) (16.6%) or greater.
- Not intended for phased construction.

DIMENSIONS:

POWERply HE FR Plus is a 4.0 mm thick membrane. Roll covers 100 sq. ft. (9.29 m²) when applied, with roll dimensions of 1m x 10.5 m (39-3/8" x 34'5"). Each roll weighs approximately 110 lbs. (50 kg).

PACKAGING:

POWERply HE FR Plus is available in pallets only, with 20 rolls per pallet.

GENERAL APPLICATION DATA:

Roof replacement usually involves more complexities that new construction roofing. Often encountered are situations such as rusted/deteriorated decks, rotted wood components, rooftop equipment which

cannot be moved or shut down, and numerous other conditions.

The following application information is designed to serve as a general guide. Your local Tremco Representative will prepare detailed specifications based on the condition of your roof.

STRUCTURAL DECKS:

Must be properly designed and structurally sound.

DRAINAGE:

Ponding conditions are unacceptable and will adversely affect the performance of any roofing system. If positive drainage does not exist, water removal from the roof surface must be facilitated by lowering drains, and/or installing additional drains tapered insulation, or Tremco approved cellular concrete system.

INSULATION :

Insulation must be dry and kept dry. No more insulation shall be installed that can be covered that day. The use of the FAS-n-FREE Adhesive for solvent free, fastener free insulation attachment is the preferred method of attachment unless otherwise specified.

INSTALLATION PROCEDURES:

According to job specifications, prepare the surface to be covered:

- Replace areas of wet insulation, deteriorated deck and wood components.
- Install roof insulation or nailed base sheet and multi-ply base ply system.

Plan the placement of POWERply HE FR Plus to ensure that water flows over or along, but not against, the exposed edges.

Starting at the low point of the roof, apply a uniform and continuous application of adhesive according to specifications. Embed ply sheets as specified. Avoid walking on plies during placement.

Place POWERply HE FR Plus in a uniform and continuous application of adhesive. Side laps 4" (100mm) minimum; end laps 6" (150 mm) minimum. Press the membrane into the adhesive using a minimum 75 pound weighted roller to assure full contact of the back of the membrane into the adhesive. Offset laps

PRODUCT ADVANTAGES	
Features	Benefits
Polymer modified asphalt	<ul style="list-style-type: none"> • Resists thermal shock and splitting
High elongation polyester reinforced	<ul style="list-style-type: none"> • Strong yet very pliable to resist tears and splits • Works with the polymer-modified asphalt blend to enhance membrane performance
Factory applied surfacing	<ul style="list-style-type: none"> • Saves job site labor and application errors

TREMCO

Roofing & Weatherproofing Peace of Mind™

from base laps. Stagger ends 36" (1m) minimum. To assure complete and uniform adhesion, adhesive should exude past lap edges. Install flashings as specified.

THERMastic, THERMastic 80, and Premium IV Asphalt are recommended as adhesives for POWERply HE FR Plus. Hot applied modified bitumen membranes require special application techniques under cool ambient temperatures and/or moderate wind conditions. Consult your local Tremco Representative for specific recommendations.

POWERply Standard Cold Adhesive, POWERply Rubberized Cold Adhesive, and BURmastic Adhesive SF are the recommended cold process membrane adhesives for use with POWERply HE FR Plus. Relax POWERply HE FR Plus in 10' to 16' sections for 60 minutes minimum just prior to application in cold adhesives when ambient temperatures are below 55°F (13°C).

PRECAUTIONS:

User must read container labels and Material Safety Data Sheets for health and safety precautions prior to use.

AVAILABILITY AND COST:

Contact your local Tremco Representative for pricing and availability. For the name and number of your Representative, call the Roofing Division at 216/292-5000.

MAINTENANCE:

Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

GUARANTEE/WARRANTY:

Tremco Incorporated warrants POWERply HE FR Plus to be free of defects and to meet published physical properties when cured and tested according to ASTM and Tremco Standards. Under this warranty, any POWERply HE FR Plus that is proved to be defective when applied in accordance with our written instructions and in applications recommended by Tremco as suitable for this product will be replaced with like product at no charge. THIS IS BUYERS SOLE AND EXCLUSIVE REMEDY.

All claims concerning product defects must be made in writing within twelve (12) months of shipment. The absence of such claims in writing during this period will constitute a waiver of all claims with respect to such product.

This warranty is IN LIEU of any and all other warranties expressed or implied, including but not limited to, any implied warranty of MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

TECHNICAL SERVICES:

Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions

TYPICAL PHYSICAL PERFORMANCE CHARACTERISTICS		
POWERply® HE FR Plus		
Property	Typical Value	Test Method
Thickness	0.160 in (4.0 mm)	ASTM D5147
Tensile strength @0°F (-18°C)	165 lbf/in MD (28.8 kN/m) 140 lbf/in XMD (24.5 kN/m)	ASTM D5147
Elongation @ 0°F (-18°C)	50% MD 50% XMD	ASTM D5147
Tear Strength	160 lbf MD (711 N) 140 lbf XMD (622 N)	ASTM D5147
Low temperature flexibility	-25°F (-32°C)	ASTM D5147

and needs to develop recommendations for special applications. The services of the Tremco Research center, which has earned a unique reputation in weatherproofing technology, complement and extend the services of the Tremco Technical Service staff.

STATEMENT OF POLICY AND RESPONSIBILITY:

Tremco takes responsibility for the furnishing of quality roofing materials, and providing specifications and recommendations for their proper installation. As neither Tremco itself nor its Representatives practice architecture or engineering, Tremco offers no opinion on, and expressly disclaims any responsibility for soundness of any structure on which its products may be applied. If questions arise as to the soundness of a structure or its ability to support a planned installation properly, the Owner should obtain the opinion of competent structural engineers before proceeding. Tremco accepts no liability for any structural failure or for resultant damages, and no Tremco Representative is authorized to vary this disclaimer.



3735 Green Road
Beachwood, OH 44122
216-292-5000

220 Wicksteed Ave
Toronto, ONT M4H 1G7
416-421-3300

6995 Printed in USA Rev. 4/16