

POWERply® Plus HT FR

A Fire Rated, Granule Surfaced, High Tensile Fiberglass Reinforced SBS/SEBS/SIS Modified Bitumen Membrane

Composition: POWERply® Plus HT FR is a granule surfaced modified bitumen membrane with fire resistant characteristics. It consists of specially selected bitumens, modified with compatible SBS/SEBS/SIS elastomers and reinforced with a combination fiberglass mat and scrim core. POWERply Plus HT FR is furnished with a factory applied white granule surfacing. POWERply Plus HT FR is asbestos free. POWERply Plus HT FR exceeds the requirements of ASTM D 6163, Type III.

Basic Uses: POWERply Plus HT FR is designed for applications in hot applied asphalt adhesives over multi-ply systems where a high strength fiberglass reinforced, granule surfaced membrane is desired. In addition, POWERply Plus HT FR is suitable for application in a cold process modified bitumen system. POWERply Plus HT FR roof systems are fire rated by Underwriters Laboratory for an external fire hazard.

Limitations:

- Not intended to perform under ponding conditions. Positive drainage required.
- Not to be exposed to solvents, oils, or other contaminants harmful to asphaltic materials.
- Backnail on roofs with slopes 2:12 (2" per foot) (16.6%) or greater.
- Not intended for phased construction.

Dimensions: POWERply Plus HT FR is a 3.4 mm (134 mil) thick membrane. Roll covers 100 sq. ft. (9.29 m²) when applied, with roll dimensions of 3' x 38' (0.91m x 11.5m). Each roll weighs approximately 95 lbs (43.1 kg).

Product Advantages	
Features	Benefits
Polymer modified asphalt	• Resists thermal shock and splits
High strength fiberglass mat and scrim	• Excellent strength and toughness
Fire resistant	• Meets building code and insurance requirements
Factory applied surfacing	• Saves job site labor prevents application errors
UL Classified	• Fire Protection



Packaging: POWERply Plus HT FR is available in pallets only, with 20 rolls per pallet.

General Application Data:

Roof replacement usually involves more complexities than new construction roofing. Often encountered are situations such as rusted/deteriorated decks, rotted wood components, rooftop equipment which cannot be moved or shut down, and numerous other conditions.

The following application information is designed to serve as a general guide. Your local Tremco Representative will prepare detailed specifications based on the condition of your roof.

Structural Decks:

Must be properly designed and structurally sound.

Drainage:

Ponding conditions are unacceptable and will adversely affect the performance of any roofing system. If positive drainage does not exist, water removal from the roof surface must be facilitated by lowering drains, and/or installing additional drains, tapered insulation, or Tremco approved lightweight insulating concrete system.

Insulation:

Insulation must be dry and kept dry. No more insulation shall be installed that can be covered that day. The use of FAS-n-FREE Adhesive for solvent free, fastener free insulation attachment is the preferred method of attachment unless otherwise specified.

Installation Procedures: According to job specifications, prepare the surface to be covered:

Replace areas of wet insulation, deteriorated deck and wood components.

Install roof insulation or nailed base sheet and multi-ply base ply system.

Plan the placement of POWERply Plus HT FR to ensure that water flows over or along, but not against, the exposed edges. Starting at the low point of the roof, apply a uniform and continuous application of adhesive according to specifications. Embed the ply sheet(s) as specified. Avoid walking on plies during the placement.

TREMCO

Roofing & Weatherproofing Peace of Mind™

For cold process applications, cut the POWERply Plus HT FR in 16' to 18' (4.9 to 5.5 m) lengths maximum. Allow lengths to relax for the following time length prior to installation:

- Above 55°F(13°C): 30 minutes
- Below 55°F(13°C): 60 minutes

For hot applications, the adhesive temperature must be at the EVT or 425°F (218°C) at the point of application, whichever is greater. THERMastic, THERMastic 50, POWERply Modified Hot Melt Adhesive, and Premium IV Asphalt are recommended as hot applied adhesives for POWERply Plus HT FR. Hot applied modified bitumen membranes require special application techniques under cool ambient temperatures and/or moderate wind conditions. Consult your local Tremco Representative for specific recommendations.

Place the POWERply Plus HT FR in a uniform and continuous application of adhesive. Press the membrane into the adhesive using a minimum 75 pound weighted roller to assure full contact of the back of the membrane into the adhesive.

Side laps 4" (102 mm) minimum; end laps 6" (152 mm) minimum. Offset membrane laps from the ply sheet laps. Stagger end laps at least 36" (914 mm). To assure complete adhesion at lap edges, adhesive should be visible past lap edges. Install flashings as specified.

Coverage Rates:

Hot melt interply application rate: 25 lbs/ 100ft² (1.24 kg/m²) Cold process interply application rate: 2 gal/SQ (0.8 L/m²)

Precautions:

Users must read container labels and Material Safety Data Sheets for health and safety precautions prior to use.

Availability and Cost:

Contact your local Tremco Roofing Representative for pricing and availability. For the name and number of your Representative, call the Roofing Division at 216-292-5000.

Maintenance:

Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

Guarantee/Warranty: Tremco Incorporated warrants POWERply Plus HT FR to be free of defects and to meet published physical properties when tested according to ASTM and Tremco standards. Under this warranty, any product that is proved to be defective when applied in accordance to our written instructions, and in applications recommended by Tremco as suitable for this product will be replaced with like product at no charge. THIS IS BUYERS SOLE AND EXCLUSIVE REMEDY.

All claims concerning product defects must be made in writing within twelve (12) months of shipment. The absence of such claims in writing during this period will constitute a waiver of all claims with respect to such

Physical Performance Characteristics		
POWERply® Plus HT FR		
Property	Typical Value	Test Method
Thickness	3.4 mm (134 mils.)	ASTM D 5147-02a
Elongation at 0°F (-18°C)	6.4% MD 6.0% XMD	ASTM D 5147-02a
Tensile Strength @ 77°F (25°C)	220 lbf/in MD (28.5 kN/m) 220 lbf/in XMD (29.4 kN/m)	ASTM D 5147-02a
Elongation at 77°F (25°C)	6.4% MD 7.0% XMD	ASTM D 5147-02a
Tear strength at 77°F (25°C)	280 lbf MD (1315 N) 300 lbf XMD (1195 N)	ASTM D 5147-02a
Low Temp Flex	-25°F (-31°C)	ASTM D 5147-02a
Dimensional Stability	pass	ASTM D 5147-02a
Compound Stability at 215°F (102°C)	pass	ASTM D 5147-02a

product. This warranty shall be IN LIEU OF any other warranty, express or implied, including but not limited to, any implied warranty of MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

Technical Services: Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the services of the Tremco Technical Service staff.

Statement of Policy and Responsibility: Tremco takes responsibility for furnishing quality materials and for providing specifications and recommendations for their proper installation. As neither Tremco itself nor its Representatives practice architecture or engineering, Tremco offers no opinion on, and expressly disclaims any responsibility for the soundness of any structure on which its products may be applied. If questions arise as to the soundness of a structure or its ability to support a planned installation properly, the Owner should obtain the opinion of competent structural engineers before proceeding. Tremco accepts no liability for any structural failure or for resultant damages, and no Tremco Representative is authorized to vary this disclaimer.



3735 Green Road
Beachwood, OH 44122
216-292-5000

220 Wicksteed Ave
Toronto, ONT M4H 1G7
416-421-3300