

Primer/Splice Wash LV

VOC Compliant Primer For Self-Adhering Uncured Flashing & Cured Cover Strip

Composition: Primer/Splice Wash LV is a VOC compliant solvent-based primer designed to be used to prepare surfaces of single ply membrane for bonding with Uncured Flashing and Cured Cover strip. Primer/Splice Wash LV is asbestos free.

Basic Uses: Primer/Splice Wash LV was specifically developed for use with EPDM single ply roofing membrane. However, it can be used with most types of single ply membranes as a wash to clean and prime membrane in one operation prior to applying self-adhering tapes.

Limitations:

- Apply at temperatures over 40° F (4° C)
- Do not apply over wet surfaces
- When stored below 40° F (4° C), warm Primer/Splice Wash LV at room temperature 72° F (22° C) for at least three days before using.
- Must be mixed before and during use.
- Do not dilute

Color: Clear

Packaging: 1 Gallon (3.78L)

Storage Life: Nine months stored indoors, out of direct sunlight, in original unopened container between 60° F (15° C) and 80° F (26.6° C).

Product Advantages	
Features	Benefits
VOC compliant	• Meets air quality regulations
Combination primer/wash	• Reduces labor cost
Rapid drying	• Increase speed of application
Increases adhesion	• Immediate bond

Surface Preparation: Surface must be clean, dry, free of dirt, oil, debris, dust, and other contaminants.

Application: Scrub the surface of the membrane with a clean Scotch-Brite pad (manufactured by 3M) saturated with Primer/Splice Wash LV. Membrane surfaces should appear wet while scrubbing. Apply Primer/Splice Wash LV to an area wider than the actual width being bonded to insure bonding to primed surfaces. When the pad becomes dirty, discard appropriately and use a fresh pad. The primed surface must be dry to the touch before tape products can be applied.

Coverage: 200-250 sq.ft./gal (0.8 to 1.0 L/m²)

Precautions: Use Primer/Splice Wash with adequate ventilation. Users must read container labels and Material Safety Data Sheets for health and safety precautions prior to use.

Availability and Cost: Contact your local Tremco Roofing Representative for pricing and availability. For the name and number of your Representative, call the Roofing Division at 216/292-5000.

Maintenance: Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

Guarantee/Warranty: Tremco Inc. warrants Primer/Splice Wash to be free of defects and to meet published physical properties when tested according to ASTM and Tremco standards. Under this warranty, any Primer/Splice Wash product that is proved to be defective when applied in accordance to our written instructions, and in applications recommended by Tremco as suitable for this product will be replaced with like product at no charge. THIS IS BUYERS SOLE AND EXCLUSIVE REMEDY.



Roofing & Weatherproofing Peace of Mind™

All claims concerning product defects must be made in writing within twelve (12) months of shipment. The absence of such claims in writing during this period will constitute a waiver of all claims with respect to such product. This warranty shall be IN LIEU OF any other warranty, express or implied, including but not limited to, any implied warranty of MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

Technical Services: Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the services of the Tremco Technical Service staff.

Statement of Policy and Responsibility: Tremco takes responsibility for furnishing quality materials and for providing specifications and recommendations for their proper installation.

As neither Tremco itself nor its Representatives practice architecture or engineering, Tremco offers no opinion on, and expressly disclaims any responsibility for the soundness of any structure on which its products may be applied. If questions arise as to the soundness of a structure or its ability to support a planned installation properly, the Owner should obtain the opinion of competent structural engineers before proceeding. Tremco accepts no liability for any structural failure or for resultant damages, and no Tremco Representative is authorized to vary this disclaimer.

Physical Performance Characteristics		
Primer/Splice Wash LV		
Property	Typical Value	Test Method
Viscosity	20-120 CPS	Brookfield RVT Spindle no. 2 at 50 rpm.
Density	9.7 lbs/gal (1160 kg/m ³)	ASTM D 1475-98
Non-Volatile Content	4.0-6.0%	ASTM D 1644-01
Color	Clear Amber	
Flash Point	< 0°F	ASTM D 3278-96
VOC	250g/L	ASTM D 3960-02
Asbestos Content	None	EPA 600/R-93/110

TREMCO

3735 Green Road
Beachwood, OH 44122
216-292-5000

An **RPM** Company

220 Wicksteed Ave
Toronto, ONT M4H 1G7
416-421-3300

R00-568
Printed in USA

Rev. 2/03