

Rubberized BURmastic® Adhesive

Cold Applied Rubberized Adhesive For Use With BURmastic Ply Sheets

Composition: Rubberized Burmastic® Adhesive is a proprietary SEBS modified asbestos free cold process asphalt interply and surfacing material.

Basic Uses: Rubberized Burmastic Adhesive is designed for application as a cold process interply adhesive and protective flood coat with BURmastic Roofing Systems. Rubberized BURmastic Adhesive can also be used in other built-up roof systems as a protective flood coat.

Limitations:

- Not intended to perform under ponding conditions. Positive drainage required.
- Not to be used as an insulation adhesive.
- Not to be exposed to solvents, oils, or other contaminants harmful to asphaltic materials.

- Not for use over expanded polystyrene (EPS) or EPS composite insulations installed in any configuration unless EPS is encapsulated within lightweight insulating cellular concrete.
- Backnail felts on roofs with slopes 2:12 (2" per foot) or greater. Do not install on roofs with slopes greater than 4:12 (4" per foot).

Grade: Spray/brush/squeegee. Spray application requires the use of an oil-jacketed heat exchange unit.

Equipment:

Spray:

Pump: Pneumatic or hydraulic pump with a minimum 2200 psi material output pressure. Output flow rate must be 3 GPM (gallons per minute) or greater for efficient production rates.

Spray tip/fluid hose: Reversible spray tip with 0.052" to 0.072" orifice and a 40° to 60° spray fan. Material fluid hose must be properly rated for the maximum working pressure of the pump being used.

Heat Exchange Unit: In-line, thermostat controlled heat transfer unit, capable of warming material to a maximum temperature of 100°F (38°C). Follow recommendations from equipment manufacturer on operation.

Squeegee: Triangular notched to provide 40-50 mil thick uniform application.

Clean-Up: Mineral spirits.

Packaging: Available in 5 (19L) and 53 (200L) gallon containers.

Storage Life: One year in unopened containers.

General Application Data: Roof replacement usually involves more complexities than new construction roofing. Often encountered are situations such as rusted/deteriorated decks, rotted wood components, rooftop equipment which cannot be moved or shut down, and numerous other conditions.

The following application information is designed to serve as a general guide. Your local Tremco Representative will prepare detailed specifications based upon your roof's conditions.

Structural Decks: Must be properly designed and structurally sound.

Drainage: Ponding conditions are unacceptable and will adversely affect performance of any roofing system. If positive drainage does not exist, water removal must be facilitated by lowering drains and/or installing additional drains, tapered insulation, or a Tremco approved cellular concrete slope system.

Product Advantages	
Features	Benefits
Cold-applied	<ul style="list-style-type: none"> • No open kettles or smoke associated with hot applied roof work. • Reduces equipment needs and start-up time • Adhesion not temperature dependent
Low odor/asbestos free	<ul style="list-style-type: none"> • Can be readily used in restrictive areas, including schools and hospitals
High performance rubberized adhesive	<ul style="list-style-type: none"> • Welds ply sheets, forming monolithic membrane
Multi-ply	<ul style="list-style-type: none"> • Redundant levels of protection and waterproofing
Not red label	<ul style="list-style-type: none"> • Shipping, storage, and handling of adhesive can be completed with few restrictions at lower costs
Versatile/flexible application	<ul style="list-style-type: none"> • Can be used in limited access areas



Roofing & Weatherproofing Peace of Mind™

Insulation: Insulation must be dry and kept dry. No more insulation shall be installed than can be covered that day. The use of Fas-n-Free Adhesive for fastener free solvent free insulation attachment is the preferred method of securement unless otherwise specified.

Acceptable Insulations:

Type	Minimum Thickness*	Facer
Wood Fiber	1/2" (13mm)	Asphalt coated
Fibrous glass	3/4" (19mm)	Paper
Isocyanurate	1" (25mm)	Black

- Insulation board must be designated by the manufacturer as suitable for roofing application.
- Maximum size: 4' x 8' (1219mm x 2438mm)

* Minimum thickness for application of Rubberized Burmastic Adhesive. Follow insulation manufacturer's instructions to obtain minimum thickness for spanning metal deck ribs.

Installation Procedures: According to particular project specifications, prepare surface to be covered:

- Replace areas of wet insulation, deteriorated deck, and wood components.
- Install roof insulation or base sheet.

Plan placement of Rubberized Burmastic Roofing System to ensure that water flows over or along, but not against exposed edges.

Starting a low point of roof, embed approved ply sheets in a uniform continuous application of Rubberized Burmastic Adhesive. Ply shall never touch ply.

Interply application rate:

Felt	Gal/100 ft ²	L/m ²
BURmastic Composite Ply	2.5	1.0
BURmastic Glass Ply	3	1.2
Approved ASTM D 4601-91	3	1.2
Type II glass base sheet		

SURFACING OPTIONS

Gravel: Apply Rubberized Burmastic Adhesive over roof surface at 5 gal/100 ft² (2.0 L/m²). Immediately broadcast 400-500 lb/100 ft² (19.4-24.4 kg/m²) of new, clean aggregate into adhesive. Aggregate shall conform to ASTM D 1863-93.

Smooth Surface: Consult with your local Tremco Representative for specific applications suitable for your geographic area.

Precautions: Users must read container labels and Material Safety Date Sheets for health and safety precautions prior to use.

Availability and Cost: Contact your local Tremco Roofing Representative for pricing and availability. For the name and number of your Representative, call the Roofing Division at 216/292-5000.

Maintenance: Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

Physical Performance Characteristics

Rubberized BURmastic® Adhesive

Property	Typical Value	Test Method
Asbestos content	None	EPA 600/R-93/116
Viscosity @ 77°F	40,000-200,000 cP (40-200 Pa•s)	ASTM D 2196-86 (1991)
Density @ 77°F	8.1 lb/gal (0.97 kg/L)	ASTM D 1475-90
Nonvolatile content	72%	ASTM D 4479-93
Asphalt content, min.	50%	ASTM D 4479-93
Flash point	>100°F	ASTM D 93-93
Uniformity & Consistency	Pass	ASTM D 4479-93

Guarantee/Warranty: Tremco Inc. warrants Rubberized Burmastic Adhesive to be free of defects and to meet published physical properties when tested according to ASTM and Tremco standards. Under this warranty, any BURmastic Adhesive product that is proved to be defective when applied in accordance to our written instructions, and in applications recommended by Tremco as suitable for this product will be replaced with like product at no charge. THIS IS BUYER'S SOLE AND EXCLUSIVE REMEDY. All claims concerning product defects must be made in writing within twelve (12) months of shipment. The absence of such claims in writing during this period will constitute a waiver of all claims with respect to such product. This warranty shall be IN LIEU OF any other warranty, express or implied, including but not limited to, any implied warranty of MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

Technical Services: Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weather-proofing technology, complement and extend the services of the Tremco Technical Service staff.

Statement of Policy and Responsibility: Tremco takes responsibility for furnishing quality materials and for providing specifications and recommendations for their proper installation.

As neither Tremco itself nor its Representatives practice architecture or engineering, Tremco offers no opinion on, and expressly disclaims any responsibility for the soundness of any structure on which its products may be applied. If questions arise as to the soundness of a structure or its ability to support a planned installation properly, the Owner should obtain the opinion of competent structural engineers before proceeding. Tremco accepts no liability for any structural failure or for resultant damages, and no Tremco Representative is authorized to vary this disclaimer.



**3735 Green Road
Beachwood, OH 44122
216-292-5000**

An **RPM** Company

**220 Wicksteed Ave
Toronto, ONT M4H 1G7
416-421-3300**