

# SF BURmastic® Adhesive

## Cold Applied Adhesive for Use with BURmastic Ply Sheets, POWERply Base Plies and POWERply MB Cap Sheets

**Composition:** SF BURmastic' Adhesive is a proprietary asbestos free, fibrated, solvent free cold process asphalt interply adhesive.

**Basic Uses:** SF BURmastic Adhesive is designed for application as a cold process interply adhesive with BURmastic Roofing Systems and PowerPly MB Systems.

**Limitations:**

- Not to be used as an insulation adhesive.
- Not to be used as a flood coat.
- Not to be exposed to solvents, oils, or other contaminants harmful to asphaltic materials.
- Not intended for use in adhering cold applied BUR systems or MB systems directly to isocyanurate insulation; the use of an approved cover board over isocyanurate insulation is recommended.
- Not for use over expanded polystyrene (EPS) or EPS composite insulations installed in any

configuration unless EPS is encapsulated within lightweight insulating cellular concrete.

- Not intended for use as smooth roof coating.
- Backnail felts on roofs with slopes 2:12 (2" per foot) or greater. Do not install on roofs with slopes greater than 4:12 (4" per foot).

**Grade:** Squeegee only.

**Equipment:**

**Squeegee:** Triangular notched to provide 32-40 mil thick uniform application.

**Clean-Up:** Mineral spirits, xylene.

**Packaging:** Available in 19L (5 gallon) containers.

**Storage Life:** Six months in unopened containers.

**General Application Data:** Roof replacement usually involves more complexities than new construction roofing. Often encountered are situations such as rusted/deteriorated decks, rotted wood components, rooftop equipment which cannot be moved or shut down, and numerous other conditions. The following application information is designed to serve as a general guide. Your local Tremco Representative will prepare detailed specifications based upon your roof's conditions.

**Structural Decks:** Must be properly designed and structurally sound.

**Drainage:** Ponding conditions are unacceptable and will adversely affect performance of any roofing system. If positive drainage does not exist, water removal must be facilitated by lowering drains and/or installing additional drains, tapered insulation, or a Tremco approved cellular concrete slope system.

**Insulation:** Insulation must be dry and kept dry. No more insulation shall be installed than can be covered that day.

**Acceptable Insulations:**

Type	Minimum Thickness*	Facer
Wood Fiber	1 3mm (1/2")	Asphalt coated
Fibrous glass board	1 9mm (3/4") 6mm (1/4")	Paper Gypsum Treated fiberglass

Product Advantages	
Features	Benefits
Cold-applied	<ul style="list-style-type: none"> <li>• No flames, hot kettles, smoke, or fire risks</li> <li>• Reduces equipment needs and start-up time</li> <li>• Adhesion not temperature dependent</li> </ul>
Low odor/asbestos free/ Solvent free	<ul style="list-style-type: none"> <li>• Can be readily used in restrictive areas, including schools and hospitals</li> </ul>
High performance adhesive	<ul style="list-style-type: none"> <li>• Welds ply sheets, forming monolithic membrane</li> </ul>
Multi-ply	<ul style="list-style-type: none"> <li>• Shipping, storage, and handling of adhesive can be completed with few restrictions at lower costs</li> </ul>
Versatile/flexible application	<ul style="list-style-type: none"> <li>• Can be used in limited access areas</li> </ul>
UL & FM approval pending • Fire protection	

# TREMCO

Roofing & Weatherproofing Peace of Mind™

- Insulation board must be designated by the manufacturer as suitable for roofing application.
- Maximum size: 1 219mm x 2438mm (4' x 8')
- \* Minimum thickness for application of SF BURmastic Adhesive. Follow insulation manufacturer's instructions to obtain minimum thickness for spanning metal deck ribs.

**Installation Procedures:** According to particular project specifications, prepare surface to be covered:

- Replace areas of wet insulation, deteriorated deck, and wood components.
- Install roof insulation or base sheet.

Plan placement of SF BURmastic Roofing System to ensure that water flows over or along, but not against exposed edges.

Starting a low point of roof, embed approved ply sheets in a uniform continuous application of SF BURmastic Adhesive. Ply shall never touch ply.

**Interply application rate:**

Felt	Gal/1 00 ft <sup>2</sup>
BURmastic Composite Ply	2.0
BURmastic Glass Ply	2.0
MB Cap Sheets	2.0

**SURFACING OPTIONS**

**Smooth Surface:** Consult with your local Tremco Representative for specific applications suitable for your geographic area.

**Precautions:** Users must read container labels and Material Safety Data Sheets for health and safety precautions prior to use.

**Availability and Cost:** Contact your local Tremco Roofing Representative for pricing and availability. For the name and number of your Representative, call the Roofing Division at 416/421-300 or 800/263-6046 or in the U.S. at 216/292-5000 or 800/852-6013.

**Maintenance:** Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

**Guarantee/Warranty:** Tremco Inc. warrants SF BURmastic Adhesive to be free of defects and to meet published physical properties when tested according to ASTM and Tremco standards. Under this warranty, any SF BURmastic Adhesive product that is proved to be defective when applied in accordance to our written instructions, and in applications recommended by Tremco as suitable for this product will be replaced with like product at no charge. THIS IS BUYER'S SOLE AND EXCLUSIVE REMEDY.

All claims concerning product defects must be made in writing within twelve (12) months of shipment. The absence of such claims in writing during this period will constitute a waiver of all claims with respect to such product.

**Physical Performance Characteristics**

**SF BURmastic® Adhesive**

Property	Typical Value	Test Method
Asbestos content	None	EPA 600/R-93/116
Viscosity @ 25°C (77°F)	17,000-25,000	ASTM D 2196-86 (1991)
Density @ 25°C (77°F)	8.8	ASTM D 6511-00
Solid/weight%	96.4%	
VOC	<40 g/l	ASTM D 6511-00

This warranty shall be IN LIEU OF any other warranty, express or implied, including but not limited to, any implied warranty of MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

**Technical Services:** Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weather-proofing technology, complement and extend the services of the Tremco Technical Service staff.

**Statement of Policy and Responsibility:** Tremco takes responsibility for furnishing quality materials and for providing specifications and recommendations for their proper installation.

As neither Tremco itself nor its Representatives practice architecture or engineering, Tremco offers no opinion on, and expressly disclaims any responsibility for the soundness of any structure on which its products may be applied. If questions arise as to the soundness of a structure or its ability to support a planned installation properly, the Owner should obtain the opinion of competent structural engineers before proceeding. Tremco accepts no liability for any structural failure or for resultant damages, and no Tremco Representative is authorized to vary this disclaimer.



An RPM Company

3735 Green Road  
Beachwood, OH 44122  
216-292-5000

220 Wicksteed Ave  
Toronto, ONT M4H 1G7  
416-421-3300