

## A Tar-Based Roof Cement for Low Slope Roofing and Roof Repairs

**Composition:** Tremfix® is composed of coal-tar pitch, reinforcing fibers, and plasticizers blended for year-round roof repair. Tremfix is asbestos free. Tremfix meets ASTM D5643, the Standard Specification for Asbestos Free Coal Tar Roof Cement.

**Basic Uses:** Tremfix is used for general repairs on coal-tar roofs, including breaks and blisters. Tremfix can be used effectively for emergency repairs on wet roof surfaces of both asphalt and coal-tar BUR. Added strength can be obtained by using reinforcing membranes.

**Limitations:** Not intended for vertical surfaces or pronounced slopes.

Not for use on EPDM, PVC, TPO, or PIB single ply roof membranes.

**Packaging:** Tremfix is available in 3 gallon (11.3L) containers.

**Grade:** Trowel

**Storage Life:** Up to one year in unopened container.

**Application Data:** Remove loose gravel, dirt, dust, rotted felt, and foreign matter. Apply over clean, sound, dry base for permanent repairs. Temporary emergency repairs can be applied over wet surfaces.

**Coverage:** 12 gal/100 ft<sup>2</sup> (4.8 L/m<sup>2</sup>) in a single troweled layer at approximately 1/8" (3 mm) thickness, or 25 ft<sup>2</sup>/5 gallon pail in a 3 course (mastic, reinforcement, mastic) application.

Rates will vary depending on ambient temperature and actual surface conditions.

**Precautions:** Users must read and follow container labels and Material Safety Data Sheets for instructions and health and safety precautions prior to and during use.

**Availability and Cost:** Contact your local Tremco Roofing Representative for pricing and availability. For the name and number of your Representative, call the Roofing Division at 216/292-5000.

**Maintenance:** Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

**Guarantee/Warranty:** Tremco Inc. warrants Tremfix to be free of defects and to meet published physical properties when tested according to ASTM and Tremco standards. Under this warranty, any Tremfix product that is proved to be defective when applied in accordance to our written instructions, and in applications recommended by Tremco as suitable for this product will be replaced with like product at no charge. THIS IS BUYERS SOLE AND EXCLUSIVE REMEDY. All claims concerning product defects must be made in writing within twelve (12) months of shipment. The absence of such claims in writing during this period will constitute a waiver of all claims with respect to such product. This warranty shall be IN LIEU OF any other warranty, express or implied, including but not limited to, any implied warranty of MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

Product Advantages	
Features	Benefits
Adheres to wet surfaces	<ul style="list-style-type: none"><li>• Emergency repairs can be made immediately</li><li>• Minimizes water damage</li></ul>
Easily troweled	<ul style="list-style-type: none"><li>• Can be used on rough surfaces</li></ul>

**Technical Services:** Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the services of the Tremco Technical Service staff.

**Statement of Policy and Responsibility:** Tremco takes responsibility for furnishing quality materials and for providing specifications and recommendations for their proper installation.

As neither Tremco itself nor its Representatives practice architecture or engineering, Tremco offers no opinion on, and expressly disclaims any responsibility for the soundness of any structure, or any component below the building structure on which its products may be applied. If questions arise as to the soundness of a structure, its ability to support a planned installation properly, or whether material below the structure will be disturbed, the Owner should obtain the opinion of competent structural engineers before proceeding. Tremco accepts no liability for any failure of the structure or material below the structure or for resultant damages, and no Tremco Representative is authorized to vary this disclaimer.

<b>Physical Performance Characteristics</b>		
<b>Tremfix®</b>		
<b>Property</b>	<b>Typical Value</b>	<b>Test Method</b>
Asbestos content	None	EPA 600/R-93/116
Viscosity @ 77 °F (25° C)	480,000-1,000,000 cP (480-1,000 Pa•s)	ASTM D 2196
Density @ 77°F (25° C)	9.1 lb/gal (1.09 kg/L)	ASTM D 1475
Nonvolatile matter, min	73%	ASTM D 4022
Behavior at 140°F (sag resistance)	1/8 inch (3 mm) max	ASTM D 4586
Adhesion to wet surface, min	75%	ASTM D 3409
Volatile organic compound (less water, less exempt solvent)	<300 g/l	ASTM D 3960



3735 Green Road  
Beachwood, OH 44122  
216-292-5000

220 Wicksteed Ave  
Toronto, ONT M4H 1G7  
416-421-3300