

# Tremco SA Underlayment

## Self-Adhesive Roofing Underlayment



### FEATURES

- Synthetic facer does not support mold growth
- Excellent weather withstanding capabilities
- Self sealing compound to ensure nail sealing
- High temperature resistance up to 225° F
- Bitumen seam locks at the edges for total watertightness
- Enhanced adhesion with new super tack self-adhesive compounding technology

### BENEFITS

- Temporary protection from elements until roof is installed
- Protection of your building should there be wind damage
- Provides a textured walkable surface for contractors
- Can be left exposed for up to 180 days

### DESCRIPTION AND USE

Tremco SA Underlayment is a self-adhesive underlayment used as a secondary water barrier under metal, asphalt shingles, slate & tiles. It consists of a highly versatile bitumen compound with enhanced adhesion which helps it to stick to most surfaces like plywood, OSB, concrete, wood particle and gypsum cover boards. It's surfaced with a tough woven polymer laminate surface which gives it excellent walkability. The adhesive compound and the tough surface together acts to provide excellent high temperature resistance which enables long exposures to weathering.

### ROLL SPECIFICATION

Color:	Grey
Surface film:	Polypropylene woven mat
Release film :	Silicon coated split release
Length:	67 feet (20.42 m)
Width:	36 inches (0.91 m)
Gross area covered:	2 squares
Weight / square:	23 lbs (10.4 kg)
Rolls per pallet:	30 rolls
Pallet weight:	1576 lbs (714.8 kg)



### PHYSICAL PERFORMANCE

Physical Properties	Test Method	Typical Value
Nominal Thickness	ASTM D 5147	40 mil (1 mm)
Tensile strength (lbf/inch)	ASTM D 1970	(MD/CD) 80/60 (14/10.5 kN/m)
Tear Resistance (Lbf)	ASTM D 1970	(MD/CD) 60/40 (267/178 kN/m)
Elongation (%)	ASTM D 1970	(MD/CD) 70/60
Adhesion to Plywood (Lbf)	ASTM D 903	5@40F, 12@75F
Nail sealability	ASTM D 1970	Pass
Thermal Stability	ASTM D 1970	Pass
Low Temp Flexibility	ICC AC 48	Pass
Water Permeance (PERMS)	ASTM E 96	0.03

# Tremco SA Underlayment

## INSTALLATION

Check the local building codes also for adequate guidance on the application. In all instances, the local building codes will take precedence and ambiguity in application methodology should be clarified with the Tremco technical team.

The state of Florida requires the underlayment to be installed in accordance with the provisions of Sections 1507 and 1518 of the FBC.

Application temperature - above 40° F and below 110° F

## SURFACE PREPARATION

- Application should only be carried out in dry weather.
- Primer is not required if the substrate is free of dust, oil or other debris
- Tremco SA Underlayment can be applied on metals, plywood, OSB, FRT plywood and insulation boards
- If applying to gypsum coverboards, priming with Tremprime QD LO/Tremprime LV is required.
- Remove existing layers if the application is on old roof. All damaged or rotted deck boards should be replaced.

## INSTALLATION

- Unroll the Tremco SA Underlayment and cut suitable workable lengths
- Relax pieces for 3-5 minutes prior to installation.
- Start at the lowest point of the roof wherever possible with lower edge of Tremco SA Underlayment flush with the outside of the primed edge. Ensure that the selvage is on the top side to maintain watertightness.
- Fold the membrane half way and peel off the release film. Stick the bare sheet firmly on to the substrate by applying pressure. Once completed release the other half and stick the membrane firmly to the substrate.
- An over lap of 3 inches should be maintained for all subsequent layers being applied.
- Its advisable to install the roof coverings over the underlays as early as possible.

## GENERAL PRECAUTIONS

- Do not apply on wet surfaces or damp surfaces.
- The membrane should be applied by a professional Roofer who has prior experience.
- Ensure that the applied Tremco SA Underlayment surface is free of wrinkles or folds before application of Roofing material
- Remove release films from the roof immediately after application as it can be slippery if left around the roof.
- Adhesive strength is reduced when applied at low temperatures. In Warm weather applications above 100F keep the product in a shaded cooler area prior to installation.
- The membrane should be patched with a smaller piece cut from the same membrane if a fastener is removed. The membrane will not self heal such openings.
- Tremco SA Underlayment is a vapor and moisture barrier and therefore the spaces under the roof deck should be properly ventilated.
- All necessary precautions should be taken while working on Tremco SA Underlayment. Necessary safety equipment and fall prevention steps should be used to avoid any fall injuries.

## STORAGE

Tremco SA Underlayment membranes must be stored indoors in a shaded area on wooden pallets neatly covered by a thick fabric and tied securely in a manner that will minimize exposure to sunlight & UV. The membrane shall be protected from all sources of heat. The shelf life is 12 months if stored as per recommendations. Excessive exposure to sunlight, UV and other sources of heat will result in considerable deterioration of the product and reduce its shelf life.



Roofing & Building Maintenance

3735 Green Road  
Beachwood, Ohio 44122

220 Wicksteed Avenue  
Toronto, Ontario, M4H 1G7

[www.tremcoroofing.com](http://www.tremcoroofing.com)

1.800.852.6013

Tremco Roofing and Building  
Maintenance is part of Tremco  
Construction Products Group.

Tremco is a US Registered trademark of Tremco CPG Inc.

The information provided on this data page supersedes all previous data concerning this product and its application. The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.