

# POWERply® Endure® 200 FR

A Fire Rated, Granule Surfaced, Polyester Reinforced SBS Modified Bitumen Membrane



## FEATURES

SBS elastomer enhanced with Reactive Enhanced Terpolymer (RET) and Thermoplastic Polyurethane (TPU)

Factory applied surfacing protected with Granulock™

Roof ID™ chip embedded into each roll

UL Classified

## BENEFITS

Improves durability of the modified bitumen blend

Increases granule retention to enhance longevity of the membrane

Capability to identify the membrane and its QC data over the life of the roof system

Fire Protection

## DESCRIPTION

POWERply Endure 200 FR is asbestos free, granule surfaced, modified bitumen membrane with fire resistant characteristics. It consists of specially selected bitumens, modified with SBS rubber along with RET and urethane high performance elastomers and reinforced with a non-woven polyester mat. It is furnished with a factory applied white granule surfacing and a clear UV cured surface treatment designed to improve granule retention.. POWERply Endure 200 FR exceeds the requirements of ASTM D 6164, Type II, Grade G and CSA A123.23, Type B, Grade 1. POWERply Endure 200 FR roof systems are rated by Underwriters Laboratories for an exterior fire hazard. Refer to UL Roofing Materials and Systems Directory for applicable system configuration.

## BASIC USES

POWERply Endure 200 FR is designed for roof membrane and flashing applications in hot applied asphalt adhesives over multi-ply systems where a high strength, polyester reinforced, granule surface membrane is desired. In addition, POWERply Endure 200 FR is suitable for application in cold process modified bitumen system.

## PACKAGING

POWERply Endure 200 FR is a 3.8mm (150 mil) thick membrane. Roll covers 100 sq. ft. (9.29 m<sup>2</sup>) when applied, with roll dimensions of 39-3/8" x 34'5" (1m x 10.5m), and weighs approximately 109 lbs (49.4 kg).

POWERply Endure 200 FR is available in pallets only, with 20 rolls per pallet.

## APPLICATION

According to job specifications, prepare the surface to be covered:

Replace areas of wet insulation, deteriorated deck and wood components.

Install roof insulation or nailed base sheet and multi-ply base ply system.

Plan the placement of POWERply Endure 200 FR to ensure that water flows over or along, but not against, the exposed edges. Starting at the low point of the roof, apply adhesive uniformly and continuously according to specifications. Embed the membranes as specified. Avoid walking on plies during the placement.

For cold process applications, cut the POWERply Endure 200 FR in 16' to 18' (4.9 to 5.5 m) lengths, maximum. Allow lengths to relax for the following time length prior to installation:

Above 55° F (13° C): 30 minutes

Below 55° F (13° C): 60 minutes

For hot applications, the adhesive temperature must be at the EVT or 425° F (218° C) at the point of application, whichever is greater. THERMastic, THERMastic 80, and Premium IV Asphalt are recommended as hot applied adhesives of POWERply Endure 200 FR. Hot applied modified bitumen membranes require special application techniques under cool ambient temperatures and/or moderate wind conditions. Consult your local Tremco Roofing sales representative for specific recommendations.

# POWERply® Endure® 200 FR

## APPLICATION CONTINUED

Place the POWERply Endure 200 FR in a uniform and continuous application of adhesive. For cold process applications press the membrane into the adhesive using a weighted roller 35-75 lbs. (16-34 kg.) to assure full contact of the back of the membrane into the adhesive.

Side laps 4" (102 mm) minimum; end laps 6" (152 mm) minimum. Hot air welding of laps is acceptable. Offset membrane laps from the base membrane. Install flashing as specified.

## COVERAGE RATES

Hot melt interply application rate: 25 lbs/ 100ft<sup>2</sup> (1.24 kg/m<sup>2</sup>). Cold process interply application rate: 2 gal/SQ (0.8 L/m<sup>2</sup>)

## LIMITATIONS

- Not intended to perform under ponding conditions. Positive drainage required.
- Not to be exposed to solvents, oils, or other contaminants harmful to asphaltic materials
- Backnail on roofs with slopes 2:12 (2" per foot) (16.6%) or greater
- Not intended for phased construction

## PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUE	TEST METHOD
Thickness	3.8 mm (150 mils.)	ASTM D 5147
Tensile Strength @ 0°F (-18°C)	165 lbf/in MD (28.8 kN/M) 140 lbf/in XMD (24.5 kN/M)	ASTM D 5147
Elongation @ 0°F (-18°C)	50% MD 50% XMD	ASTM D 5147
Tensile Strength @ 77°F (25°C)	130 lbf/in MD (22.6 kN/M) 110 lbf/in XMD (19.2 kN/M)	ASTM D 5147
Elongation @ 77°F (25°C)	55% MD 60% XMD	ASTM D 5147
Tear Strength @ 77°F (25°C)	160 lbf MD (711 N) 140 lbf XMD (622 N)	ASTM D 5147
Low Temp Flex	-40° F (-40° C)	ASTM D 5147
Dimensional Stability	pass	ASTM D 5147
Compound Stability @ 215°F (102°C)	pass at 302° F (150° C)	ASTM D 5147
Granule Loss	0.2g	ASTM D 5147

## PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

## TECHNICAL SUPPORT

Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the service of the Tremco Service Staff.



[www.tremcoroofing.com](http://www.tremcoroofing.com)  
3735 Green Road  
Beachwood, Ohio 44122  
1.800.852.6013

220 Wicksteed Avenue  
Toronto, Ontario, M4H 1G7  
1.800.668.9879

Tremco Roofing and Building  
Maintenance is part of Tremco  
Construction Products Group.

Tremco is a US Registered trademark of Tremco CPG Inc.  
The information provided on this data page supersedes all previous data concerning this product and its application.  
The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.